

Government of the People's Republic of Bangladesh
Chemical Laboratory
Custom House, Chattogram.
Web: www.chc.gov.bd/reports
E-mail: chcchemi.laboratory@gmail.com


Scanned
28 JUN 2021

Subject: Chemical Test Report.

Sample Received On: 24.06.2021 Sample Code No:

Date of Delivery: Test Report No: 2588

01	B/E No. & Date	:	C-981594, Date-16.06.2021.
	File No. & Date	:	
02	Name of Section	:	Section-AIR
03	Declared Commodity Name as per Invoice/CRF	:	Invoice Item 1. Polyurethane in primary form (Takelac PP-9680) (Sample: 02 Boyums)
04	Method of Test/Analysis	:	Phy.tests C/PUI test etc.
05	Physical & Chemical Properties & Ingredients Found	:	Pale yellow viscous liquid, Pungent odour, Insoluble in H ₂ O. Soluble in COS. Sp.gr. > 1gm/cm ³ P ^H =7. IBP=77°C C/PUI test=+Ve. Ingredients: Hydroxyl group (-OH) terminated polyurethane, Organic Solvents.
06	Result of Physical /Chemical Test/Analysis	:	The supplied sample is hydroxyl group terminated "Polyurethane in primary form."
07	Probable use of Imported Goods.	:	It may be used as Laminating Adhesive after proper mixing with hardener (Takenate I-7000).
08	Comments (If any)	a	
		b	


28.6.2021
Signature of Examiner
Md. Abdul Hannan
Chemical Examiner
Custom House, Chattogram.

- Notes: i. The results described here are based only on the supplied sample(s) in this laboratory.
ii. Complain or query regarding test report(s) should be lodged within one month of report delivery date.
iii. The laboratory is not responsible for the data quality affected due to sampling, transporting and storage conditions of the sample(s) maintained before received in the laboratory.
iv. This report or any part of this should not be published without prior approval of the authority.

Government of the People's Republic of Bangladesh
Chemical Laboratory
Custom House, Chattogram.
Web: www.chc.gov.bd/reports
E-mail: chcchemi.laboratory@gmail.com


Scanned
28 JUN 2021

Subject: Chemical Test Report.

Sample Received On: 24.06.2021 Sample Code No:

Date of Delivery: Test Report No: 2588

01	B/E No. & Date	:	C-981594, Date-16.06.2021.
	File No. & Date	:	
02	Name of Section	:	Section-AIR
03	Declared Commodity Name as per Invoice/CRF	:	Invoice Item 2. Polyurethane Hardener (Takenate I-7000) (Sample: 02 Boyums)
04	Method of Test/Analysis	:	Phy. tests C/PUI test etc.
05	Physical & Chemical Properties & Ingredients Found	:	Pale yellow viscous liquid. Pungent odour. Insoluble in water. Soluble in COS. Sp.gr. > 1gm/cm ³ pH=7. IBP=75°C -NCO test=+Ve. Ingredients: isocyanate group (-NCO) terminated polyurethane prepolymer, Diphenylmethane diisocyanate, Toluene diisocyanate, Ethyl Acetate.
06	Result of Physical /Chemical Test/Analysis	:	The supplied sample is isocyanate group terminated polyurethane " Hardener. "
07	Probable use of Imported Goods.	:	It is used as hardener for preparing laminating adhesive after proper mixing with polyurethane (Takelac PP-9680).
08	Comments (If any)	a	


28.6.2021
Signature of Examiner
Md. Abdul Hannan
Chemical Examiner
Custom House, Chattogram.

- Notes: i. The results described here are based only on the supplied sample(s) in this laboratory.
ii. Complain or query regarding test report(s) should be lodged within one month of report delivery date.
iii. The laboratory is not responsible for the data quality affected due to sampling, transporting and storage conditions of the sample(s) maintained before received in the laboratory.
iv. This report or any part of this should not be published without prior approval of the authority.